



# 250W Polycrystalline Solar Module

Revolutionary Product
--Selective Emitter™ Solar Module
Same module size,
Same exposure time,
More power output!



MORE-LESS=? You know how to choose!


#### **Features**

- High conversion efficiency;
- Low power tolerance of ±3%;
- Excellent performance under low lighting conditions;
- Low hot spot effect, due to low reverse current density;
- Low degradation under light exposure;
- Low cell performance mismatch during encapsulation, our SE module demonstrates high power output, which is very close to the power generated by the whole cells before encapsulation;
- Passing mechanical load test of 5400Pa according to IEC 61215(advanced test);
- Tested to withstand hails with maximum diameter of 25mm and impact speed of 23m/s;
- Blacksheet is also available.










Selective Emitter cell



Conventional cell

### To one solarcell, the main factors that affect conversion efficiency are as:

- The number of minority carriers crossing the PN junction in unit time;
- The electrical resistivity of metal electrode.

## SE solar cell adopts deep and shallow junction tructures, which mainly improve conversion efficiency from some aspects such as:

- The shallow junction with light diffusion of cell active areas make the number of minority carrier through PN junction more than common;
- 2. The voltage between the deep and shallow junctions of metal contact area increases the power of minority carriers;
- 3. The deep junction with heavy diffusion of metal electrode areas ensure the lower contact resistance between metal and semiconductor.





#### **Technical Parameters SSS250W-poly**

| Product Type                              | SSS 250   |  |
|---|---|--|
| Parameter                                 | Typical Data  |  |
| Watts Peak (W)                            | 250   |  |
| Open Circuit Voltage (V)                  | 37.8  |  |
| Short Circuit Current (A)                 | 8.78  |  |
| Optimum Operating Voltage (V)             | 29.95   |  |
| Optimum Operating Current (A)             | 8.36  |  |
| Silicon Cell Efficiency                   | 17.5%   |  |
| Voltage Temperature Coefficient           | -0.35%/K  |  |
| Current Temperature Coefficient           | +0.06%/K  |  |
| Power Temperature Coefficient             | -0.47%/K  |  |
| Quantity of Calla                         | 60  |  |
| Quantity of Cells                         | Poly-crystalline silicon cell series connection             |  |
| Maximum System Voltage(V)                 | 1000 (TUV)/600(UL)  |  |
| Module Safe Wire Current (A)              | 10  |  |
| Module Insulating Resistance(Ω)           | ≥100MΩ  |  |
| Parameter Physical Size(mm <sup>3</sup> ) | 1640×990×40(L×W×H)  |  |
| Module Operating Temperature(°C)          | -40°C to +90°C  |  |
| Hail                                      | maximum diameter of 25mm <sup>-1</sup> with impact speed of |  |
| Паш                                       | 23.0m.s <sup>-1</sup>                                       |  |
| Maximum Surface Load Capacity             | tested up to 2,400Pa according to IEC 61215                 |  |
| Weight                                    | 18.5kg  |  |

#### Notes:


- 1. Test conditions: irradiation intensity:  $1000W/m^2$ , AM1.5; Battery temperature:  $25\pm2^{\circ}\mathbb{C}$ , deviation of Wp(W)  $\pm5\%$ , deviation of Voc(V), Isc(A), Vm(V) and Im(A)  $\pm10\%$ .
- 2. In the column of product type, M stands for polycrystalline Frame: Aluminium Anodizes Alloy Output tolerace: +/-5%
- 3. Warranty: 2 years Modul,10 years for 90 % the power, 25 years 80% the power







# 1640\*990\*40



#### **Quality and Certificates**

- 5-year hardware warranty;
- 25-year power output warranty\*\*\*.
- Certifications;

| Certification Authority | Test Standard            | Power Range |
|-------------------------|--------------------------|-------------|
| TÜV Rheinland           | IEC61215                 | 40W-200W    |
| ASU-PTL                 | IEC61215                 | 155W-185W   |
| VDE                     | IEC61215<br>IEC61730-1/2 | 155W-180W   |
| CSA                     | UL1703                   | 155W-195W   |



Average efficiency of 17.5%, up to 18%.

<sup>\*\*\* 10</sup> years at 90% of the minimal rated power output, 25 years at 80% of the minimal rated power output.



<sup>\*\*</sup> Compared to modules with the same size, made of normal P-type solar cells , average efficiency of which is 16%.